

SMS-100 - Metric Tube - Longitudinally Welded in 6 Metre Lengths - Type 316L and Type 304L

Inside	Wall	Weight	Pressure	Product	Product
Diameter	Thickness	Per Metre	Rating in Bar	Code	Code
'A' mm	'B' mm	Kilos	at 20 Deg C	316L	304L
15	1.50	0.62	215	100A015150	100B015150
20	1.50	0.81	168	100A020150	100B020150
25	1.50	1.00	138	100A025150	100B025150
32	1.50	1.26	110	100A032150	100B032150
40	1.50	1.56	90	100A040150	100B040150
50	1.50	1.93	73	100A050150	100B050150
50	2.00	2.60	95	100A050200	100B050200
65	1.50	2.50	57	100A065150	100B065150
65	2.00	3.41	74	100A065200	100B065200
80	1.50	3.06	48	100A080150	100B080150
80	2.00	4.11	64	100A080200	100B080200
100	1.50	3.81	39	100A100150	100B100150
100	2.00	5.11	51	100A100200	100B100200
100	3.00	7.74	77	100A100300	100B100300
125	1.50	4.75	31	100A125150	100B125150
125	2.00	6.36	41	100A125200	100B125200
150	1.50	5.69	26	100A150150	100B150150
150	2.00	7.61	34	100A150200	100B150200
150	3.00	11.49	51	100A150300	100B150300
200	1.50	7.57	19	100A200150	100B200150
200	2.00	10.12	26	100A200200	100B200200
200	3.00	15.25	39	100A200300	100B200300
250	2.00	12.62	21	100A250200	100B250200
300	2.00	15.12	17	100A300200	100B300200
300	2.50	18.94	21	100A300250	100B300250
350	2.50	22.07	18	100A350250	100B350250
400	3.00	30.27	19	100A400300	100B400300
450	3.00	34.03	12	100A450300	100B450300
500	3.00	37.78	11	100A500300	100B500300
600	3.00	45.29	9	100A600300	100B600300
700	4.00	70.51	10	100A700400	100B700400
800	4.00	80.52	9	100A800400	100B800400
900	4.00	90.54	8	100A900400	100B900400
1000	4.00	100.55	7	100AA10004	100BB10004
1200	4.00	120.68	6	100AA12004	100BB12004